

Synthesis and Application of C-Dot - The Material for the Future

Sardar S and Bandyopadhyay A*

Department of Polymer Science and Technology, University of Calcutta, India



***Corresponding author:** Abhijit Bandyopadhyay, Department of Polymer Science and Technology, University of Calcutta, Kolkata-700009, India

Submission: 📅 June 10, 2021

Published: 📅 June 18, 2021

Volume 2 - Issue 1

How to cite this article: Sardar S, Bandyopadhyay A. Synthesis and Application of C-Dot - The Material for the Future. *Polymer Sci Peer Rev J.* 2(1). PSPRJ. 000529. 2021.

Copyright@ Bandyopadhyay A, This article is distributed under the terms of the Creative Commons Attribution 4.0 International License, which permits unrestricted use and redistribution provided that the original author and source are credited.

Abstract

In this mini review, we have tried to highlight various synthetic routes of carbon dot (C-dot) and their applications. We have mentioned both top-down and bottom up approaches and substrate requirement for its synthesis and specific properties that the resultant C-dots is going to display. New age applications like energy harvesting and storage, coloured lighting etc. of C-dots are also stated in this review.

Keywords: C-dot; Carbon; Synthesis; Graphite; Electro-chemical fields; Organic compounds

Introduction

C-dot has been regarded as one of the most useful and interesting nanomaterial among the contemporary nanomaterials because of its unique features such as excellent photo luminescent property, outstanding biocompatibility, long cycle life, light weight, small size, unique physical characteristics, easy aqueous dispersibility and pH sensitivity [1]. The number of scholarly articles published on C-dot is steadily increasing in number covering its expanded field of applications. As of now, C-dots have been explored as agents for bio imaging, sensing, photo catalysis, electro catalysis, fluorescent ink, light emitting diode, and solar cells [2].

Mini Review

Chemical structure of C-dot varies on the route adopted for its synthesis. It typically has a size of a few nanometers and has molecular weight of a few thousand to tens of thousands of times that of bigger particles. The surface often contains a variety of functional groups such as -OH, -COOH and -NH₂, which makes them water dispersible and also boosts their ability to polymerize forming various inorganic, organic, or physiologically active molecules [3]. The synthesis of C-dot can be done in a variety of ways. This may be divided into two categories: "top-down" and "bottom-up" procedures. With the aid of arc-discharge, electrochemical synthesis, laser-ablation, and chemical oxidation, the "top-down" approach breaks bulk carbon materials such as carbon nanotubes, graphite, candle soot, and activated carbon into C-dots [2]. However, no definite substrate is required for the bottom-up technique. In this case, it is made from a variety of organic compounds through carbonization using plasma treatment, hydrothermal or acidic oxidation reactions, microwave, and carbonizing organics [4]. All of these aforementioned techniques need complex experimental settings, and they are also difficult techniques for the creation of luminous C-dots as well. As a result, green techniques are critically explored for the manufacture of C-dots particularly for opto-electronic applications. Researchers are now banking on soy milk, chicken eggs, plant leaves, pomelo peel, grass, and other inexpensive or readily accessible natural resources as precursors for the production of C-dots to make the process cheap and more viable. Electro-Luminescence (ECL) features are found to be pronounced in the synthesized C-dots as well. Graphite has also been found to produce C-dots with enhanced Electro-luminescence behaviour. In that case, the C-dots are produced through electrochemical oxidation of graphite. Since the potential cycle is maintained between +1.8 and -1.5V, the resultant C-dots display an enhanced Electro-luminescence property having the maximum at 535nm. When C-dot is dispersed in ethanol,

the dual ECL signal is often observed (TBAB). Except for certain recent studies on electrochemical abilities in the context of electro-synthesis, electro-catalysis, and sensing of C-dots, only a little study has been done on the electrical characteristics of C-dots so far [5].

Recently, formation of C-dot based polymer composites has been reported whereby epoxy resin, agarose gel, and iono gels have been used as the matrix and the resultant composites are targeted for diverse luminescent hues and white light generation [6]. Energy production/storage at low cost have been the priority of the current era. Due to the abundance of trap states, C-dots exhibit charge entrapment properties. As a result, they are advantageously

employed as an electrical capacitor. Since the practical demonstration of the quantum size impact on photoluminescence of C-dots and the theoretical prediction of quantum confinement, it has received a lot of attention in optoelectrical and photovoltaic technologies in the last few years. They have the potential to still improve the efficiency with which sunlight is converted into energy. C-dots are also attracting a lot of attention as a light-harvesting material for solar cells. Energy harvesting reduces CO₂ emissions which in other way lowers the renewable energy cost. (Figure 1) summarizes the synthesis and application fields of C-dots through a schematic [7]. The synthesis procedure and their subsequent application is demonstrated in tabular form (Table 1), [8].

Table 1: The source and their application of C-dots [8].

Sl. No.	Source Molecule	Mode of Synthesis	Application
1	Carbon soot	Chemical oxidation	Bio-imaging
2	Graphite powder	Laser ablation	Bio-imaging
3	Urea, polyethylene glycol (PEG)	Hydrothermal treatment	Bio-imaging
4	Carbon nanotubes and graphite	Electrochemical	Bio-imaging
5	Glucose	Carbonization	Bio-imaging
6	Carbon nanopowder	Electrochemical	Drug/gene delivery
7	Citric acid and ethylenediamine	Hydrothermal treatment	Drug/gene delivery
8	Sorbitol and sodium hydroxide	Hydrothermal treatment	Drug/gene delivery
9	Fullerenes (C60)	Ultrasonic	Bio-sensing
10	L-Glutamic acid	Pyrolysis	Bio-sensing
11	Citric acid and melamine	Pyrolysis	Bio-sensing
12	Lactose and NaOH	Simple heating	Bio-sensing
13	EDTA	Hydrothermal treatment	Chemical-sensing
14	Citric acid and triethylamine	Hydrothermal treatment	Chemical-sensing
15	Graphite rods	Electrochemical	Chemical-sensing
16	Ascorbic acid and glycol	Ultrasonic treatment	Chemical-sensing
17	Glucose	Hydrothermal treatment	Degradation of Dye
18	Carbon-based	Hydrothermal treatment	CO ₂ Photo-reduction
19	Graphite/Vitamin C/Citric acid	Microwave synthesis	H ₂ generation
20	Dopamine	Hydrothermal treatment	Targeted Hella cell




Figure 1: Schematic of synthesis and different applications of C-dots.

Conclusion

In conclusion, it can be said that C-dots are going to be the key material in near future to address the key issues like energy harvesting and storage, low cost lighting, diagnostic etc. either in sole form or in the form of flexible polymer composites. It is thus important to explore its structure-property relationship for extracting more benefits in opto-electrical and electro-chemical fields.

References

1. Song Y, Zhu S, Shao J, Yang B (2017) Polymer carbon dots-A highlight reviewing their unique structure, bright emission and probable photoluminescence mechanism. *J Polym Sci Part A Polym Chem* 55(4): 610-615.
2. Jlassi K, Eid K, Sliem MH, Abdullah AM, Chehimi MM, et al. (2020) Rational synthesis, characterization, and application of environmentally friendly (polymer-carbon dot) hybrid composite film for fast and efficient UV-assisted Cd²⁺ removal from water. *Environ Sci Eur* 32: 12.
3. Yang S, Zhang Y, Xue Y, Lu S, Yang H, et al. (2020) Cross-linked polyamide chains enhanced the fluorescence of polymer carbon dots. *ACS Omega* 5(14): 8219-8229.
4. Woo J, Song Y, Ahn J, Kim H (2020) Green one-pot preparation of carbon dots (CD)-embedded cellulose transparent film for Fe³⁺ indicator using ionic liquid. *Cellulose* 27: 4609-4621.
5. Aziz SB, Abdullah OG, Brza MA, Azawy AK, Tahir DA (2019) Effect of carbon nano-dots (CNDs) on structural and optical properties of PMMA polymer composite. *Results Phys* 15: 102776.
6. Putro PA, Yudasari N, Isnaeni, Maddu A (2021) Spectroscopy study of polyvinyl alcohol/carbon dots composite films. *Walailak J Sci Technol* 18: 1-12.
7. Ve A, Dergisi D, Dinc S, Kara M (2018) Synthesis and applications of carbon dots from food and natural products: A mini-review. *J Apitherapy Nature* 1(1): 33-37.
8. Sharma A, Das J (2019) Small molecules derived carbon dots: Synthesis and applications in sensing, catalysis, imaging, and biomedicine. *J Nanobiotechnology* 17: 1-24.

For possible submissions Click below:

[Submit Article](#)